



AO4710 (≥ 92%)

2023.04.03

SPECIFICATIONS

- ▶ Chemical formula: Al_2O_3
- ▶ Chemical name: Aluminium oxide
- ▶ Appearance: Dense sintered aluminum oxide
- ▶ Main characteristics: High mechanical strength, high temperature resistance, high frequency insulation, high chemical resistance, wear resistant
- ▶ Main applications: Liner, pulverizer
- ▶ Colour: White

MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

Density		[g/cm ³]	JIS R 1634	3.6
Water absorption		[%]	JIS C 2141	0
Vickers hardness HV9.807N		[GPa]	JIS R 1610	11.8
Flexural strength 3 P.B.		[MPa]	JIS R 1601	390
Compressive strength		[MPa]	JIS R 1608	-
Young's modulus of elasticity		[GPa]	JIS R 1602	280
Poisson's ratio		[-]	JIS R 1602	0.23
Fracture toughness (SEPB)		[MPa*m ^{0.5}]	JIS R 1607	-
Coefficient of linear thermal expansion	40 - 400 °C	[*10 ⁻⁶ /K]	JIS R 1618	7.1
	40 - 800 °C			7.9
Thermal conductivity		[W/(m*K)]	JIS R 1611	16
Specific heat capacity		[J/(g*K)]	JIS R 1611	0.79
Thermal shock temperature difference		[°C]	JIS R 1648	200
Dielectric strength		[kV/mm]	JIS C 2141	16
Volume resistivity	20 °C	[Ω*cm]	JIS C 2141	>10 ¹⁴
	300 °C			10 ¹²
	500 °C			10 ⁹
Dielectric constant		-	JIS C 2141	8.9
Dielectric loss angle		[*10 ⁻⁴]	JIS C 2141	6
Loss factor		[*10 ⁻⁴]	JIS C 2141	53

The values are typical material properties and may vary according to products configuration and manufacturing process. For more details, please feel free to contact us.

KYOCERA Fin ceramics Europe GmbH

E-Mail: info@kyocera-fin ceramics.de · www.kyocera-fin ceramics.de