

# Nelco<sup>®</sup> Advanced Circuitry Materials

## Nelco<sup>®</sup> N7000-2 VO

### Toughened Polyimide Laminate & Prepreg

*The Nelco N7000-2 VO series is a next-generation high-Tg polyimide using a toughened resin chemistry to achieve a UL 94-V0 designation. This advanced material is designed for use in a wide variety of applications that include fine geometry multilayer constructions and extreme reliability.*

#### Key Features

##### Polyimide resin chemistry

- Robust Thermal Stability and Reliability
- Toughened resin system
- High temperature tolerances

##### Lead-free assembly compatibility

- Withstands multiple thermal excursions
- Tg 250°C by DSC
- T260 >30 minutes
- Low Z-Axis CTE

##### Supports current and previous military and industrial standards

- Meets UL 94 V0
- Meets IPC-4101/42 specification and the laminate and prepreg properties of IPC-4101/40 and /41
- N7000-2 VO is not ANSI GPY

##### Reliable plated-through holes

- Low Z-Axis CTE providing good dimensional stability

##### Reliable processing

- Improved fracture resistance compared with traditional polyimide systems
- Reduced cure time compared to other traditional polyimide systems

##### And Much More

- Vacuum laminated
- Available in a wide variety of constructions, copper weights and glass styles.
- All Nelco materials are RoHS compliant.



#### Applications

- Fine-Line Multilayers
- Backplanes
- Surface-Mount Multilayers
- BGA Multilayers
- Avionics
- Down-well Petroleum
- Burn-in Boards

#### Global Availability

Nelco Products, Inc. (California) - Americas

+1.714.879.4293

Neltec, Inc. (Arizona) - Americas

+1.480.967.5600

Nelco Products Pte. Ltd. - Asia Pacific

+65.6861.7117

Neltec, S.A. - Europe

+33.562.98.52.90

[www.parkedelectro.com](http://www.parkedelectro.com)

[info@arkedelectro.com](mailto:info@arkedelectro.com)

**Park's UL file number: E36295**



PARK  
ELECTROCHEMICAL  
CORP.

# Nelco® N7000-2 V0

## Toughened Polyimide Laminate & Prepreg

	U.S. Units		Metric Units		Test Method
<b>Mechanical Properties</b>					
Peel Strength - 1 oz. (35 micron) Cu					
After Solder Float	5.8	lb / inch	1.001	N / mm	IPC-TM-650.2.4.8
At Elevated Temperature	5.2	lb / inch	0.91	N / mm	IPC-TM-650.2.4.8.2a
After Exposure to Process Solutions	5.7	lb / inch	0.98	N / mm	IPC-TM-650.2.4.8
X / Y CTE [-40°C to +125°C]	10 - 12	ppm / °C	10 - 12	ppm / °C	IPC-TM-650.2.4.41
Z Axis Expansion [50°C to 260°C]	1.7	%	1.7	%	IPC-TM-650.2.4.24
Young's Modulus (X / Y)	4.5 / 3.8	psi x 106	30.6 / 25.9	GN / m2	ASTM D3039
Poisson's Ratios (X / Y)	0.183 / 0.160		0.183 / 0.160		ASTM D3039
Thermal Conductivity	TBD	W / mK	TBD	W / mK	ASTM E1461
Specific Heat	TBD	J / gK	TBD	J / gK	ASTM E1461
<b>Electrical Properties</b>					
Dielectric Constant (50% resin content)					
@ 1 MHz (TFC / LCR Meter)	4.0		4.0		IPC-TM-650.2.5.5.3
@ 1 GHz (RF Impedance)	3.8		3.8		IPC-TM-650.2.5.5.9
@ 10 GHz (Stripline)	3.8		3.8		IPC-TM-650.2.5.5.5
Dissipation Factor (50% resin content)					
@ 1 MHz (TFC / LCR Meter)	0.009		0.009		IPC-TM-650.2.5.5.3
@ 10 GHz (Split Post Cavity)	0.010		0.010		
Volume Resistivity					
C - 96 / 35 / 90	10 <sup>6</sup>	MΩ - cm	10 <sup>6</sup>	MΩ - cm	IPC-TM-650.2.5.17.1
E - 24 / 125	10 <sup>8</sup>	MΩ - cm	10 <sup>8</sup>	MΩ - cm	IPC-TM-650.2.5.17.1
Surface Resistivity					
C - 96 / 35 / 90	10 <sup>6</sup>	MΩ	10 <sup>6</sup>	MΩ	IPC-TM-650.2.5.17.1
E - 24 / 125	10 <sup>6</sup>	MΩ	10 <sup>6</sup>	MΩ	IPC-TM-650.2.5.17.1
Electric Strength	1200	V / mil	4.7x104	V / mm	IPC-TM-650.2.5.6.2
Dielectric Breakdown	>50	kV	>50	kV	IPC-TM-650.2.5.6
Arc Resistance	124	seconds	124	seconds	IPC-TM-650.2.5.1
<b>Thermal Properties</b>					
Glass Transition Temperature (Tg)					
DSC (°C)	250	°C	250	°C	IPC-TM-650.2.4.25c
TMA (°C)	243	°C	243	°C	IPC-TM-650.2.4.24c
Degradation Temp (TGA) (5% wt. loss)	390	°C	390	°C	IPC-TM-650.2.4.24.6
Pressure Cooker-60 min then solder dip					IPC-TM-650.2.6.16
@288°C until failure (max 10 min.)	Pass		Pass		(modified)
T260	30+	minutes	30+	minutes	IPC-TM-650.2.4.24.1
T300	3.5	minutes	3.5	minutes	
<b>Chemical / Physical Properties</b>					
Moisture Absorption	0.32	wt. %	0.32	wt. %	IPC-TM-650.2.6.2.1
Methylene Chloride Resistance	0.40	% wt. chg.	0.40	% wt. chg.	IPC-TM-650.2.3.4.3
Density [50% resin content]	1.93	g / cm <sup>3</sup>	1.93	g / cm <sup>3</sup>	Internal Method

Park Electrochemical Corp. is a global advanced materials company which develops and manufactures high-technology digital and RF/microwave printed circuit materials and advanced composite materials, parts and assemblies. The company operates under the Nelco®, Nelcote® and Nova™ names.

All test data provided are typical values and not intended to be specification values. For review of critical specification tolerances, please contact a Nelco representative directly. Nelco reserves the right to change these typical values as a natural process of refining our testing equipment and techniques.

Aeroglide™, CoreFix®, Easycure™, EF®, EP™, LD®, Mercurywave™, Nelco®, Nelcote®, Nova™, PeelCote™, RTFoil® and SI® are trademarks of Park Electrochemical Corp.

Nelco reserves the right to make changes without further notice to any products herein to improve reliability, function or design. Nelco does not assume any liability arising out of the application or use of any product described herein; neither does it convey any license under its patent rights nor the rights of others. This disclaimer of warranty is in lieu of all warranties whether expressed, implied or statutory, including implied warranties of merchantability or fitness for a particular purpose.

